



Mastics, Coatings, Adhesives, Sealants

CHIL-JOINT[®] CP-70 Sealant

FLEXIBLE JOINT SEALANT, FLASHING COMPOUND AND VAPOR SEAL

DESCRIPTION

CHIL-JOINT[®] CP-70 is a non-shrinking, permanently flexible, economical sealant for applications with all types of low temperature, dual temperature, and some high temperature insulation systems.

USES

CHIL-JOINT CP-70 sealant is used to vapor seal and act as an expansion joint in the joints of cellular glass and cellular plastic insulations. It will not attack even polystyrene insulations and remains flexible and functional through a wide temperature range. CHIL-JOINT CP-70 sealant has good resistance to elevated temperatures, and it is recommended as an expansion joint material up to 300°F (149°C). It is an excellent water seal, vapor seal and expansion joint material, and is suggested as a joint sealant for all metal jacketing systems.

ADVANTAGES

It has practically no volatiles that would cause it to shrink when it is used to seal the joints of impermeable materials. It will not shrink or pull away from surfaces, and even at elevated temperatures (although it may discolor and harden) it still forms a tight weather bond under most conditions. It forms a tough protective surface where exposed to the air which helps protect the permanent flexibility of the underlying sealant. CHIL-JOINT CP-70 sealant requires no mixing or additives.

APPLICATION

CHIL-JOINT CP-70 sealant is applied with pointed trowel, putty knife, or power extrusion equipment. It is also available in caulking tubes and may be applied with hand or power caulking guns. It has a heavy body and can be applied in various thicknesses without sagging or running.

COLOR

Gray

WET WEIGHT

14.2 lbs./U.S. gal.
(1.7 kg/liter)

AVERAGE NON-VOLATILE

93% by volume, 96% by weight

SERVICE TEMPERATURE RANGE

(Temperature to which dry coating is subjected.)
-100°F to 300°F
-73°C to 149°C

APPLICATION TEMPERATURE RANGE

40°F to 100°F
(4°C to 38°C)

DRYING TIME

Non-Drying: Skins over in 24 hours

COVERAGE

For Joint: 1" x 1/16" = 1 U.S. gal. for 308 lin. ft. (2.5 cm x .16 cm = 24m/liter)
125 lin. ft. per 10.5 oz. tube for 1/8" bead (38m/310 ml tube for 3.2 mm bead)

FLASH POINT

142°F

COMBUSTIBILITY

Combustible. Flame spread and fuel contribution negligible when used as sealant in 1/8 in. (3.2 mm) wide joints of incombustible insulation.

CLEAN-UP

Mineral spirits

WATER VAPOR PERMEANCE ASTM E-96

0.008 perm-inch (0.013 metric per-cm) The water vapor transmission through 1 inch of impermeable insulation in 12 in. X 18 in. blocks with 1/8 in. (3.2 mm) wide joints of CP-70 us tii small to measure.

CP-70 contains no asbestos, lead, mercury, or mercury compounds.

Visit us on the web at www.fosterproducts.com



8534
11/02
DPI

Specialty Construction Brands, Inc.

Customer Service
800-231-9541

601 West Campus Drive, Suite C7
Arlington Heights, IL 6004

Fax
800-942-6856

JOINT SEALANT FOR CELLULAR GLASS OR CELLULAR PLASTIC INSULATIONS

During application of insulation apply a minimum 1/8" (.31cm) thickness of CHIL-JOINT CP-70 sealant to the longitudinal and abutting joints, for the total width of the insulation section. Sections of insulation shall be pressed firmly into place to ensure an unbroken seal. At termination of insulation, the CHIL-JOINT CP-70 sealant shall be extended back under the insulation for a minimum of 4" (10.16cm).

JOINT SEALANT FOR METAL JACKETING SYSTEMS

All joints of aluminum or stainless steel jacketing shall be weather sealed by applying a 1/8" (.31 cm) bead of CHIL-JOINT CP-70 sealant underneath the lab. Jacketing shall be firmly embedded and pulled up tight. All overflow of sealant shall be removed with solvents.

FLASHING COMPOUND AT HOT UNINSULATED SURFACES

Where weatherproofed insulation butts uninsulated surfaces, CHIL-JOINT CP-70 sealant shall be applied over the adjoining weatherproof surface and flashed to the uninsulated surface a minimum of 2 inches (5.08cm) in each direction. A glass fiber reinforcing mesh of CHIL-GLAS #10 shall be embedded into the flashing compound and the minimum flashing thickness at all points shall be 1/16" (.15 cm).

NOTES TO SPECIFYING ENGINEER

1. When using a solvent vapor barrier coating system such as ENCACEL or CHIL-PERM CP-30 LO, the joint sealant to be used shall be CHIL-BYL CP-76 sealant. CHIL-JOINT CP-70 sealant shall not be used for this application.
2. In areas where multiple layer cellular insulations are applied, it is suggested that the insulation manufacturer's recommendations be followed. All joints shall be buttered with CHIL-JOINT CP-70 sealant to a minimum thickness of 1/16" (.15 cm).

Application Guide and Suggested Procedures

1. USE OF MATERIAL

CHIL-JOINT CP-70 sealant is a very viscous material. Although it may be used at very low temperatures, it is suggested that the CHIL-JOINT CP-70 sealant be kept as warm as possible (preferably stored at 70°F; 21°C) just prior to application for optimum ease of application. **DO NOT THIN.** CHIL-JOINT CP-70 sealant should be applied at temperatures 40°F (4°C) or greater.

2. CONDITION OF THE SURFACE TO BE COATED

The surface to be coated should be free of all oil, grease, loose scale and foreign matter and shall be dry and free from frost.

3. APPLICATION

CHIL-JOINT CP-70 sealant is usually applied with a steel trowel. There is power extrusion equipment available for production applications. When using the caulking tubes and laying down a bead in the joints of block insulation or pipe insulation, sufficient beading should be applied so that when the joints are squeezed together a minimum 1/16" (.15 cm) film is formed.

4. HINTS FOR SUCCESS

When the joints of insulation are squeezed together, any excess CHIL-JOINT CP-70 sealant should be removed or smoothed down flush with the insulation surface. Spillage or overflow of CHIL-JOINT CP-70 sealant may be readily removed with almost any type of hydrocarbon solvent. Although CHIL-JOINT CP-70 sealant may be coated over with many types of coatings, user should verify by his own test that there would be no bleeding through the top coating by the CHIL-JOINT CP-70 sealant.

Make certain this product is completely dry and the area free from product odor if food is involved.

CUSTOMER SERVICE—800-231-9541 OR 800-338-2975

IMPORTANT: Specialty Construction Brands, Inc. warrants that each of its products will be manufactured in accordance with the specifications in effect on the date of manufacture. WE MAKE NO OTHER WARRANTIES AND EXPRESSLY DISCLAIM ANY WARRANTIES OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE. If a product fails to meet this limited warranty, purchaser's sole and exclusive remedy is replacement of the product or, at our option, refund of the purchase price. OUR ACCEPTANCE OF ANY ORDERS FOR THE PRODUCT IS EXPRESSLY CONDITIONAL UPON PURCHASER'S ASSENT TO THE TERMS ON THE APPLICABLE INVOICE.

ADEQUATE TESTS: The information contained herein we believe is correct to the best of our knowledge and tests. The recommendations and suggestions herein are made without guarantee or representation as to results. We recommend that adequate tests be performed by you to determine if this product meets all of your requirements. The warranted shelf life of our products is six months from date of shipment to the original purchaser.

For industrial use only. Keep out of reach of children.

Consult Material Safety Data Sheet and container label for further information.